

**3038 Black White Gray was tested and met the following flammability requirements:**

ASTM E 84 Adhered Class A



|                    |                           |                |                               |                     |                  |
|--------------------|---------------------------|----------------|-------------------------------|---------------------|------------------|
| <b>Tested For:</b> | <b>Teesha Prezeau</b>     | <b>Phone:</b>  | <b>(201) 917-7738</b>         | <b>Received:</b>    | <b>2/8/2023</b>  |
|                    | <b>Designtex</b>          | <b>Fax:</b>    |                               | <b>Completed:</b>   | <b>2/14/2023</b> |
|                    | <b>357 County Avenue</b>  | <b>Mobile:</b> |                               | <b>Code:</b>        | <b>X</b>         |
|                    | <b>Secaucus, NJ 07094</b> | <b>PO#:</b>    |                               | <b>Test Report:</b> | <b>3-50439-0</b> |
|                    | <b>USA</b>                | <b>Email:</b>  | <b>tprezeau@designtex.com</b> |                     |                  |

**Key Test:** ASTM E84/ACT

735

**Client's Identification:**

Style: DNA. Composition: 50% Cellulose, 40% Latex, 10% Polyester. Finish: None. Weight: 15 oz/lin yd. Product End Use: Wallcovering.

Test Category: Tunnel Test      Specifier: ACT      LE 2022; V 1/23 BG      PC: ME

TEST PERFORMED: ASTM E84 - Standard Test Method for Surface Burning Characteristics of Building Materials [LE 2018a; V 9/18] --

As cited by the Association of Contract Textiles (ACT) Voluntary Performance Guidelines (December 2021)

APPROXIMATE THICKNESS OF SPECIMEN (as measured by SGS North America): 0.018"

SPECIMEN WEIGHT (to include substrate when applicable):

Prior to Conditioning: 116.4 lbs.

Stabilized Weight (taken twice within 24 hours): 115.5 lbs.

PRODUCT CATEGORY:

- Textile Type Product
- Vinyl Type Product
- Other than Textile Type or Vinyl Type Product: see client's Identification section above

**BRIEF DESCRIPTION OF TEST:** This test method is used to determine the relative burning behavior of a material under defined test conditions. The test is performed in a 25 ft. long tunnel/duct-like apparatus and is often referred to as the "tunnel test". The test contemplates a calibration where Red Oak burns to the 24 ft. mark in 5.5 minutes  $\pm$  15 seconds. During the actual test, a 24 ft. long x 23" wide specimen rests horizontally in a ceiling configuration inside the test chamber facing downward and toward two upward oriented burners. A furnace lid that rests in a water trough seals the chamber tight. A cement board placed on the backside of each specimen assembly protects the furnace lid during the test. The near face of the specimen is subjected to a 4.5 ft. flame insult of approximately 88 kW for ten minutes. The time and distance of the spread of flame along the length of the specimen and the smoke developed as read by the photometric system are all recorded. The Flame Spread and Smoke Developed are reported as an Index.

CG

Ver. 2021-03-09 10:35

Page 1 of 4

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.

96 Allen Boulevard Suite D, Farmingdale, NY 11735 USA • Phone: (631) 293-8944 • Email: govmark.test.reports@sgs.com



|                    |                       |                                      |                               |
|--------------------|-----------------------|--------------------------------------|-------------------------------|
| <b>Tested For:</b> | <b>Teesha Prezeau</b> | <b>Phone:</b> (201) 917-7738         | <b>Received:</b> 2/8/2023     |
|                    | DesignTex             | <b>Fax:</b>                          | <b>Completed:</b> 2/14/2023   |
|                    | 357 County Avenue     | <b>Mobile:</b>                       | <b>Code:</b> X                |
|                    | Secaucus, NJ 07094    | <b>PO#:</b>                          | <b>Test Report:</b> 3-50439-0 |
|                    | USA                   | <b>Email:</b> tprezeau@designtex.com |                               |

**Key Test:** ASTM E84/ACT

735

## SPECIMEN MOUNTING:

- Self-supporting: The test specimen was rigid enough to be self-supporting when placed into test position. No additional support was required.
- Adhered to IRC: The test specimen was bonded to ¼" Inorganic Reinforced Cement (IRC) boards.
- Adhered to Gypsum: The test specimen was adhered to 5/8" thick Type X gypsum board.
- Unadhered: The specimen was not adhered to any substrate. Instead, it was laid over a 2" hexagonal wire mesh screen and ¼" rods.
- Other: \_\_\_\_\_

## SPECIMEN LENGTH: The 24 ft. length was comprised of:

- Continuous unbroken 24 ft. length
- Sections:  Three 8 ft. sections butted end to end  
 Three 8 ft. sections positively joined  
 Other: Five 5 ft. sections butted end to end

ADHESIVE (applied by SGS North America):  No  
 Yes (specify): Roman Pro-880

OBSERVATIONS:  No unusual observations

Burning Drips to Floor further qualified as:  Minor;  Moderate;  Major

Delamination

Sagging

Shrinkage

Fallout (specimen displacement from ceiling mount)

Other: \_\_\_\_\_

REMARKS:  None  
 Other: \_\_\_\_\_

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.



|                    |                           |                |                               |                     |                  |
|--------------------|---------------------------|----------------|-------------------------------|---------------------|------------------|
| <b>Tested For:</b> | <b>Teesha Prezeau</b>     | <b>Phone:</b>  | <b>(201) 917-7738</b>         | <b>Received:</b>    | <b>2/8/2023</b>  |
|                    | <b>Designtex</b>          | <b>Fax:</b>    |                               | <b>Completed:</b>   | <b>2/14/2023</b> |
|                    | <b>357 County Avenue</b>  | <b>Mobile:</b> |                               | <b>Code:</b>        | <b>X</b>         |
|                    | <b>Secaucus, NJ 07094</b> | <b>PO#:</b>    |                               | <b>Test Report:</b> | <b>3-50439-0</b> |
|                    | <b>USA</b>                | <b>Email:</b>  | <b>tprezeau@designtex.com</b> |                     |                  |

**Key Test:** ASTM E84/ACT

735

RESULTS: Flame Spread Index: 10  
Smoke Developed: 50

ROUNDING: Flame Spread Index value has been rounded to the nearest multiple of 5.  
Smoke Developed value has been rounded to:

| Raw Data      | Rounded                |
|---------------|------------------------|
| Less than 200 | Nearest multiple of 5  |
| 200 or more   | Nearest multiple of 50 |

ACCEPTANCE CRITERIA (as cited by ACT):

|                | Flame Spread Index | Smoke Developed |
|----------------|--------------------|-----------------|
| <b>Class A</b> | 0 - 25             | 450 or less     |

NOTE: Class A is also known as Class 1 and may be so specified in some Codes.

CONCLUSION: Based on the reported Results and cited Acceptance Criteria, the item tested:

Complies       Does not comply

DATA SUMMARY:

Time to Ignition (minutes:seconds): 00:58  
Maximum Flame Spread "Distance" (feet): 2.6  
Maximum Flame Spread "Time" (seconds): 243

CODE CLASSIFICATION: Based on the reported Results and cited Code Classification System, the item tested is assigned a:

- Class I or A rating  
 Class II or B rating  
 Class III or C rating  
 Fails to achieve a minimum classification thereby rendering the product unsuitable in terms of code requirement.  
 Based on product performance\*, ASTM E84 is not a suitable test method for the material.

\* Severe melt, drip, delamination or other behavior that destroys the continuity of the flame front such that a valid flame spread is unobtainable (See "Remarks" on Page 2 of 4.)

The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.



|                    |                       |                |                               |                     |                  |
|--------------------|-----------------------|----------------|-------------------------------|---------------------|------------------|
| <b>Tested For:</b> | <b>Teesha Prezeau</b> | <b>Phone:</b>  | <b>(201) 917-7738</b>         | <b>Received:</b>    | <b>2/8/2023</b>  |
|                    | DesignTex             | <b>Fax:</b>    |                               | <b>Completed:</b>   | <b>2/14/2023</b> |
|                    | 357 County Avenue     | <b>Mobile:</b> |                               | <b>Code:</b>        | <b>X</b>         |
|                    | Secaucus, NJ 07094    | <b>PO#:</b>    |                               | <b>Test Report:</b> | <b>3-50439-0</b> |
|                    | USA                   | <b>Email:</b>  | <b>tprezeau@designtex.com</b> |                     |                  |

**Key Test:** ASTM E84/ACT

735

## CODE CLASSIFICATION SYSTEM:

|                        | Flame Spread Index | Smoke Developed |
|------------------------|--------------------|-----------------|
| <b>Class I or A:</b>   | 0 - 25             | 450 or less     |
| <b>Class II or B:</b>  | 26 - 75            | 450 or less     |
| <b>Class III or C:</b> | 76 - 200           | 450 or less     |

LIMITATIONS OF THE ASTM E84 CLASSIFICATION SCHEME: Most building codes will accept the ASTM E84 classifications when the interior finish product is used in a sprinklered area. Certain local authorities such as NYC have more stringent requirements, i.e. Smoke Developed ranges from a maximum 25 to 100.

If the interior finish product is a textile or vinyl wall covering used in a non-sprinklered area, the NFPA 265 room corner fire test applies.

Certain products which give off excessive heat such as but not limited to cellular plastics, cellular foam (either with or without coverings as applicable), polypropylene, and high density polyethylene should be tested by NFPA 286 - Standard Methods of Fire Tests for Evaluating Contribution of Wall and Ceiling Interior Finish to Room Fire Growth. In SGS North America's opinion, the codes require NFPA 286 for such products, even in sprinklered areas.

CERTIFICATION: I certify that the reported results were obtained after testing specimens in accordance with the procedures and equipment specified above.

DocuSigned by:

*Bobby Brown*

B50EB94D593C454...

2/17/2023

AUTHORIZED SIGNATURE  
SGS NORTH AMERICA  
/jab /dv

Test Engineer: Chris Gangi

Enclosure: Graphs

DS  
*BB*



The results contained in this report relate only to the item(s) tested. The test report shall not be reproduced except in full, without written approval from SGS North America.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/terms-e-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for a maximum of 45 days only.



Program: Steiner Tunnel (Version 1.0.1.0)

Test Method : ASTM E84  
Report # : 3-50439-0-X  
Test Date : 2/14/2023  
Client : Designtex  
Operator : Chris Gangi  
Details of Preparation : The test specimen was bonded to 1/4" Inorganic Reinforced Cement (IRC) boards. The 24ft. length was comprised of five 5ft. sections butted end to end.  
Observations : No unusual observations.

**Results**

Area Under Flame Curve (ft min) : 15.95  
Raw Flame Spread Index : 8.22  
Ignition Time (mm:ss) : 00:58  
Area Under Smoke Curve (%A min) : 43.12  
Raw Smoke Developed Index : 50.80  
Total Gas Flow (ft<sup>3</sup>) : 56.8  
Maximum Flame Front Achieved (ft) : 2.6 @ 243s  
**Flame Spread Index : 10**  
**Smoke Developed Index : 50**  
**Material Classification : A**

CERTIFICATION : I certify that the above results were obtained after testing the specimens in accordance with the procedures and equipment specified by ASTM E84

*Chris Gangi*  
\_\_\_\_\_


AUTHORIZED SIGNATURE



Program: Steiner Tunnel (Version 1.0.1.0)

Test Method : ASTM E84  
Test Report # : 3-50439-0-X

### Flame Progression



### Smoke Density

